

TECHNICAL DATA SHEET SCANDITENE 3001

Revision date: 2022-02-21

IDENTIFICATION OF PRODUCT

Trade name: **Scanditene 3001**
Product numbers: **LDE291**

COMPOSITION/INFORMATION ON INGREDIENTS

CAS-no	EG-no	Components	% (per kg)	Symbol	R-phrases
9002-88-4	-	Polyethene	98. - 100	-	-
-	-	Other unidentified polymers	0 - 1.5	-	-
-	-	Other unidentified contaminants	0 - 0.5	-	-

Note: These products are made from 100 % Post-Industrial waste

PHYSICAL AND CHEMICAL PROPERTIES

The data given below are average values and will vary from batch to batch

Physical state	Solid granules				
Color	Natural, clear to translucent				
Melt flow index	0,25-0,45 g/10min	2,16kg/190°	ISO 1133		
Density	0.91-0.925 g/cm ³		ISO 1183-1A		
E - modulus	~261 N/mm ²	+23°C 1mm/min	ISO 527-2 type 1A		
Tensile strength	~14 N/mm ²	+23°C 50mm/min	ISO 527-2 type 1A		
Elongation at break	~94 %	+23°C 50mm/min	ISO 527-2 type 1A		
Elongation at yield	~81 %	+23°C 50mm/min	ISO 527-2 type 1A		
Charpy notched	82,8 kJ/m ²	+23°C / 1eA	ISO 179-1		
Ash content	0,0 %	600°C	ISO 3451-1A		

This Technical Data Sheet supersedes all earlier product and information sheets. Revision 1.4

To the best of our knowledge, the information contained in this data sheet is accurate as of the date of publication. However, REMONDIS Sweden AB does not assume any liability whatsoever for the accuracy and completeness of the information provided nor for the suitability of this material for any particular application. The information provided is the result of small-scale laboratory tests which may not provide a reliable indication of the performance or properties obtained on larger scale equipment or when used in conjunction with any other material. It is the customer's responsibility to ensure this material is suitable for use in their application and the customer shall assume all risk and liability arising from such use.